

Product Data Sheet

Astro PFP FR Acrylic

Revision 6 - 12th January 2024



0843-UKTA-23/0027 | 23/0028
0843-CPR-1319



CE-ETA - 21/0030 | 21/0031
CE-2531-CPR-CX010147

Astro PFP FR Acrylic

Fire Rated Mastic

- High end formula, certified worldwide
- Classified for fire sealing all types of construction and building service penetrations
- Very high sound insulation
- Low emissions - environmentally and user friendly
- Simple to apply with a smooth surface finish
- Permanently flexible – will accommodate movement up to 12.5%
- No priming necessary for application to most materials
- Suitable for most surfaces, included concrete, masonry, steel, gypsum, glass, plastics and most non-porous surfaces
- Hardens quickly, tack free after 1 hour (the fire performance specification of the joint filler has been derived when the joint filler has been let to cure for a month)
- **Extended** to 24 months storage time (under correct conditions)



Product Description

Designed to prevent the spread of fire and smoke through joints and openings in fire rated walls and floors (including openings formed around building service penetrations); the Astro PFP FR Acrylic will also maintain the acoustic design performance.

When subjected to atmospheric conditions, the sealant cures however, it will retain a degree of elasticity for joint movement. Under fire exposure, The Astro PFP FR Acrylic creates a robust fire seal by the formation of a durable intumescent char.

The Astro PFP FR Acrylic can be used with a suitable filling material i.e. stone wool or Astro PFP FR backing material in order to secure correct width to depth ratio, and to reduce the shrinking of the sealant during curing. Minimum depth and maximum width of the joints are included in the installation instructions.

Astroflame Fireseals Ltd
Unit 8 I.O Centre
Stephenson Road
Segensworth, Fareham
Hampshire, PO15 5RU



CE-2531-CPR-CXO10147
CE-ETA - 21/0030
CE-ETA - 21/0030
ASTRO PFP FR ACRYLIC
"See ETA - 21/0030 & 21/0031
for relevant characteristics"



0843-CPR-1319
0843-UKTA-23/0027
0843-UKTA-23/0028
ASTRO PFP FR ACRYLIC
"See UKCA - 23/0027 & 23/0028
for relevant characteristics"

Product Description

When testing pipes, one can choose not to cap (or close) the pipe, or cap the pipe inside the furnace, or outside the furnace, or on both sides. The configuration chosen depends on the intended application of the pipe and/or the installation environment.

The code defining if a pipe is capped is stated after the fire classification. For instance, EI 60 C/U which means the pipe was capped inside the furnace, and uncapped outside the furnace. The test configuration defines the approvals possible.

Our engineering judgment based on EN 1366-3:2009 are:

Intended use of pipe		Pipe end condition ⁴⁾
Rainwater pipe, plastic	At drainage	U/U ¹⁾
	Not at drainage	C/C ²⁾
Drainage or sewage pipe, plastic	Ventilated drain	U/U ¹⁾
	Unventilated drain	U/C ¹⁾
	Drain w/water trap	U/C ¹⁾
	Not at drainage	C/C ²⁾
Pipe in closed circuit (water, gas, air, electricity etc.)		C/C ^{2) 3)}
Flue gas recovery system pipe, plastic		U/C ¹⁾
Pipe with open ends and ≥ 50cm length on both sides, plastic		U/U ²⁾
Pipe supported by suspension system, metal	Fire rated support	C/U ¹⁾
	Non-fire rated	U/C ¹⁾
Waste disposal shaft pipe, metal		U/C ¹⁾

¹⁾ Suggested in EN 1366-3:2009. ²⁾ Astroflame's judgment based on tests.

³⁾ Metal pipes should have fire rated support. ⁴⁾ U/U classified fire seals cover C/U, U/C and C/C. C/U classified fire seals cover U/C and C/C. U/C classified fire seals cover C/C.

Technical Data

Condition	Ready for use, acrylic based filler
Specific gravity	1.56 – 1.60
Flash point	None
Reaction to fire	B - S1, d0
Expansion in fire	1 : 2-3
Non-sticky	Max. 75 minutes
Film forming	Max. 25 minutes
Totally hardened	3 to 5 days depending on thickness and temperature
Flexibility	12.5% in mortar/concrete/masonry EN ISO 9046
Durability	Z ₂ intended for use in internal conditions with humidity classes other than Z ₁ , excluding temperatures below 0 °C
BWR 3	Use category IA1, S/W3
Thermal conduct.	0.845 W/mK (+/- 3%) @ 20mm depth
Storage	24 months stored in unopened cartridges. To be stored in temperatures between 10°C and 30°C
Service temp.	-20 to +70°C
Application temp.	+5 to +30°C
Compatibility	Suitable for use with most materials, but should not be used in direct contact with bituminous materials
Limitations	Should not be used in permanently damp areas or in joints with high movement
Classification	CE-marked - Sealant for fire rated joints and penetrations class EI 240
Standard colours	Standard white
Colour codes	White: RAL 9002

This Technical Data Sheet and the Installation Instructions are based on the product's European Technical Assessment issued in accordance with regulation (EU) No 305/2011 on the basis of EAD 350454-00-1104 and EAD 350141-00-1106.

Availability

Product Code	Product Description	Colour	Sizes
AFPPACW	Astro PFP FR Acrylic - Cartridges	White	310 ml
AFPPACW/FOIL	Astro PFP FR Acrylic - Foil	White	600 ml

To Order & Specify

Please contact us and quote the following information - Quantity / Product Code / Product Description / Size
 Typical example:- 25 / AFPPACW / Astro PFP FR Acrylic - Cartridges / 310 ml

>> Tel: [01329 844 500](tel:01329844500) or >> Email: sales@astroflame.com

Installation

We have technical representatives who provide assistance in the selection and specification of the products on this site and should be consulted for exact installation and product suitability. Ensure an early engagement with ourselves, designers, main contractor and specialist installers before any installation. Other trades and/or manufacturers may need to be consulted. For in-depth information, specification and technical advice please call our Head Office on tel [01329 844 500](tel:01329844500) or email sales@astroflame.com

Maintenance

All interested parties, designer, specifier, main contractor and specialist installers should provide access to allow the fire stopping seals to be regularly inspected and maintained, as well as records kept of such maintenance at minimum periods of 12 months, as required by the Regulatory Reform Order, and repaired if necessary. Reference should be made to ASFP TGD 17 – Code of Practice for the Installation and Inspection of Fire Stopping.

Competency

It is vital that those entrusted to design or install a fire stopping product have the necessary levels of competence to undertake the task professionally and thoroughly. The level of competency required will be commensurate with the expected complexity of the building. All designers must eliminate, reduce or control foreseeable risks that may arise during installation, construction or maintenance when preparing or modifying designs. Clients should ensure that the principal designer and principal contractor carry out their duties under CDM regulations. The ASFP foundation course in passive fire protection provides essential knowledge as part of demonstrating competency and understanding in this key fire protection specialism.

Additional Notes

Please refer to the ETA/UKTA sheet for fields of application for this product. For further information on installation requirements please refer to the manufacturer of the services and the wall/floor specification to ensure the compatibility of this product, if in doubt please contact the technical team with services and wall/floor specification on: T: [01329 844 500](tel:01329844500) or E: sales@astroflame.com

Health and Safety

Please see (SDS) Safety Data sheet - This can be requested from our sales team T: [01329 844 500](tel:01329844500) or E: sales@astroflame.com

As part of our policy of ongoing improvements, we reserve the right to modify, alter or change product specifications without giving notice. Product illustrations are representations only. All information contained in this document is provided for guidance only, and as ASTROFLAME (FIRE SEALS) LTD has no control over the specific application or installation methods of the products, or of the prevailing site conditions, no warranties expressed or implied are intended to be given as to the actual performance of the products mentioned or referred to, and no liability whatsoever will be accepted for any loss, damage or injury arising from the use of the information given of products mentioned or referred to herein.

The above information to the best of our knowledge is true and accurate and based upon current test data and is supplied for your guidance only. Customers should satisfy themselves to the suitability of the product based on the products limitation of applications and that the product is fit for purpose for their intended use and no guarantee is given or implied since the conditions of actual use are beyond our control. ASTROFLAME (FIRE SEALS) LTD, disclaim any liability for loss, damage or other expense arising from the use of information, data or products mentioned or referred to and reserve the right to change any details or specifications without notice. If you are in any doubt as to the suitability of this product for your intended application please contact our technical team on 01329 844500 or email sales@astroflame.com and we will contact you.